

USG™ Plaster Bonder

Preparation	Surfaces should be structurally sound, clean and free from loose material, dust, dirt, oil, grease, wax, loose paint, mildew, rust or efflorescence. Glossy painted surfaces should be dulled with an abrasive. Protect adjacent finished surfaces with masking tape, soap powder emulsion or other commercial product formulated for protective use during plastering. Air temperature should be maintained at or above 45 °F (7° C). Do not apply over water-soluble materials, such as glue, calcimine, wallpaper and casein-based adhesives. Do not apply to frozen or frost-covered surfaces.
Mixing	USG™ Plaster Bonder should be applied as is. When used over highly absorptive surfaces, such as lightweight concrete block, dilution may be required, and should be made in modest increments. Excessive dilution will reduce performance and may affect stability. Product should be hand-stirred prior to use. Excessive shaking, mechanical mixing or boxing batches should be avoided to prevent entrapping of air bubbles, which will prevent continuous film application.
Application	<p>Apply uniform film over entire surface using brush, roller or spray applicator. Allow to dry one hour or until the surface is dry to the touch. Plastering can begin as soon as Plaster Bonder is dry to the touch, or delayed for up to 10 days with no effect on bond.</p> <p>Before plastering, inspect bonding agent application to ensure a continuous film. Reapply USG Plaster Bonder to any areas not satisfactorily covered. Do not apply wallpaper to newly bonded plastered surface for 90 days.</p>
Cleanup	Clean mixing containers and tools with water immediately after use.

Trademarks

The following trademarks used herein are owned by United States Gypsum Company or a related company: USG.

Note

Products described here may not be available in all geographic markets. Consult your U.S. Gypsum Company sales office or representative for information.

Notice

We shall not be liable for incidental or consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than their intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from the date it was or reasonably should have been discovered.

SAFETY FIRST!

Follow good safety practices. Read material safety data sheets and related literature on products before specification and/or installation.

