

SECTION 09 29 00 – GYPSUM BOARD, 3/4 in. (19.1 mm) USG Sheetrock® Brand Ultracode® Core Panels (UL Type ULTRACODE)

Product Summary:

- 3/4 in. (19.1 mm) Type X panels that reduce labor and material costs
- Feature a noncombustible gypsum core that is encased in 100% recycled face and back papers that form a high strength composite design
- Can provide 1-4 hr. fire ratings with fewer layers of gypsum panels than are typically required when used in approved applications
- Comply with ASTM C1396, *Standard Specification for Gypsum Board*, for 3/4 in. (19.1 mm) and Type X gypsum wallboard
- Underwriters Laboratories Inc. (UL) Classification as to fire resistance, surface-burning characteristics and noncombustibility
- Can be used in any UL Design in which Type ULTRACODE panels are listed.
- Achieved GREENGUARD Gold Certification and qualifies as a low VOC emitting material (meets CA 01350)
- For more information, refer to product submittal sheet WB2167B or usg.com

Note to Specification Writers:

- This document is not intended to function as a standalone specification. It is intended to assist the specifier in inserting the proper language into the following recommended specification sections: 09 29 00 – GYPSUM BOARD.
- This product is manufactured at USG gypsum panel plants, reducing distances and carbon footprint for transport.
- Panels shall be installed in accordance with GA-216, *Specifications for the Application and Finishing of Gypsum Panel Products* and ASTM C840, *Standard Specification for Application and Finishing of Gypsum Board*.
- Contact USG at 800.874.4968 for technical questions.

PART 2 – GYPSUM PANEL PRODUCTS

2.1 TYPE X GYPSUM PANEL

A. ASTM C1396, *Standard Specification for Gypsum Board*, for 3/4 in. (19.1 mm) and Type X gypsum wallboard

1. Basis of Design: Subject to compliance with project requirements, the design is based on the following: United States Gypsum Company, USG Sheetrock® Brand Ultracode® Core Panels
2. UL Type Designation: “ULTRACODE”
3. ASTM E136 Noncombustibility: Meets
4. ASTM E84 Surface-Burning Characteristics
 - a. Flame Spread: 15
 - b. Smoke Developed: 0
 - c. Class A (Flame spread not greater than 25 and smoke developed not greater than 450): Meets
5. ASTM C473, *Standard Test Methods for Physical Testing of Gypsum Panel Products*
 - a. Core Hardness
 - 1) Field [Not less than 11 lbf (49 N)]: Meets
 - 2) End [Not less than 11 lbf (49 N)]: Meets
 - 3) Edge [Not less than 11 lbf (49 N)]: Meets
 - b. Flexural Strength
 - 1) Parallel [Not less than 56 lbf (249 N)]: Meets
 - 2) Perpendicular [Not less than 167 lbf (743 N)]: Meets
 - c. Nail Pull Resistance [Not less than 97 lbf (432 N)]: Meets
 - d. Humidified Deflection [Not greater than 5/8 in. (15.9 mm)]: Meets
6. Thickness: 3/4 in. (19.1 mm)
7. Length: 8-12 ft. (2438-3658 mm)
8. Width: 4 ft. (1219 mm)
9. Weight: 2.8 lb./sq. ft. (13.7 kg/sq. m.)



10. Edge: Tapered

Disclaimer: The USG Product Specifications contained herein are intended for use as product reference material by architects, engineers, other design professionals, contractors, building code officials, or other competent construction industry trade professionals having an interest in the selection, specification and use of products manufactured by the subsidiaries of USG Corporation. The specifications are intended solely as technical support incident to the sale and use of USG products and not intended to be a substitute for the design review and approval of the licensed design professionals for the project. These materials may be printed and/or transferred electronically solely as needed by the user. Because electronic files can be modified by other parties, without notice or indication of such modifications, modification of USG Product Guide Specifications is the sole responsibility of the Design Professional.