

Note: This drawing is for your records. Contractors should complete all repairs by the end of each work day.

When the roof has multiple levels, inspect one level at a time. For larger roof levels, break into smaller sections to eliminate confusion.

NOTE: USE TPO PRIMER OR LOW VOC PRIMER WITH ALL QUICK-APPLIED (QA) PRODUCTS INCLUDING VERSIGARD WHITE PEEL & STICK EPDM ACCESSORIES THAT ARE APPROVED FOR USE ON TPO SYSTEMS.

Heat Welding Procedures:

Temperature settings for automatic welder:

TPO = Recommended starting temperature and speed setting is 1004°F at 12.5'/minute for all membrane thicknesses. Adjustments may have to be made depending on test weld results.

All welds must be a minimum of 1½" wide, regardless of warranty duration.

Minimum requirements for test welds: Perform a test weld at the start of work each morning and afternoon by using like material over the same substrate. *Versico does not require the use of destructive testing.*

Once cooled, peel the test sample apart to examine delamination of the membrane from the scrim reinforcement.

Welding Troubleshooting Checklist:

- Temperature and/or speed of welder
- Outside temperature (humidity and time of day)
- Heat transfer over insulation plates
 - Cold welds/voids can be found where seams cross over plates
- Cord size and distance from power source
- Generator size and wattage
 - Minimum 6500-watt generator for 1 automatic welder
 - Minimum 3000-watt generator for 2 hand welders
- Regular service/maintenance for welder
- Cleanliness of membrane
 - Proper cleaning materials/rags
 - Weathered Membrane Cleaner for TPO membrane
- Cleanliness of automatic welder/hand welder nozzle
- Check all start and stop points thoroughly

Seams and detail work must be cooled to ambient temperature prior to probing. All probing should be completed each work day allowing time for voids to be marked and repaired by the end of the day. This ensures all the seams and detail work has been probed prior to inspection.

Please consult Versico's Specification Supplement (section T-01-18) for more information about welding procedures, generator usage, and general troubleshooting.



IMPORTANT INFORMATION:
If you need assistance, it's only one call away.

Local FSR phone number:

Additional FSR phone number(s):

Sales Representative phone number:

Technical Sales Representative phone number:

Distributor phone number(s):

As a reminder, this guide is meant to help with details commonly seen in the field. Not all details are included in this guide. Versico contractors are encouraged to call with any questions.

For assistance, please call 1-800-992-7663 and choose option 2 or ask for the Technical Department.



A SINGLE SOURCE FOR SINGLE-PLY ROOFING
800.992.7663 • www.versico.com

Versico, VersiTrim and the Versico logo are trademarks of Versico.
04.19.21 © 2021 Versico.
REPRINT CODE: 609038 VE-6980 - "TPO (Thermoplastic) Rooftop Guide/Inspection Checklist"

A SINGLE SOURCE FOR SINGLE-PLY ROOFING




TPO (Thermoplastic) Rooftop Guide/Inspection Checklist

Quick Reference

Guide for Inspecting Your System
This guide will illustrate the minimum requirements of a roof inspection and provide a basic understanding of some common details.

Below is a simple roof drawing with penetrations included. It shows the path followed by Versico Field Service Representatives (FSRs) when they inspect a roof for warranty.



- | | | | |
|--|--------------------------|--|-----------|
| | - Roof Hatch | | - Scupper |
| | - Curb | | - Drain |
| | - Pipe | | - Sleeper |
| | - Pourable Sealer Pocket | | |

- Step 1: Inspect the perimeter.**
Update the roof plan to show the location of all curbs, penetrations, drains, etc.
Focus on securement and termination.
Mark deficiencies on the roof plan as they are found.
- Step 2: Inspect all seams on the roof level.**
Focus on plate placement and proper seaming.
- Step 3: Inspect all curbs, penetrations, drains, etc.**
Focus on one detail at a time, confirming proper securement, termination, and flashing minimums.
- Step 4: Finally, walk across the roof, update areas in need of repair, and perform a general check of the system.**




Scan the QR Code to view the Inspection Quick Reference Video

Common Details

TPC-1.1 VersiTrim Drip Edge Fascia

- Is wood nailer wider than metal flange?
- Is wood nailer flush with insulation?
- A continuous cleat and the metal must be fastened 6" OC using ring shank nails.
 - Installed according to SMACNA ES-1 requirements.
- Deck flange must be completely covered by TPO PS Cover Strip with a minimum of 2" coverage past nail heads.
 - Apply TPO PS Coverstrip using TPO Primer or Low-VOC Primer.
 - Wood nailer must be securely anchored.
 - When using metal by others, the metal flange must be fastened so it does not bow prior to overlaying.



TPC-1.1 VersiTrim Drip Edge Fascia

TPC-2.0/AC-2.2 Membrane Splice


- Are all seams probed? Are all welds a minimum of 1½" wide?
- If reinforced edging is exposed, is ⅛" bead of TPO Cut-Edge Sealant present?
- For 60-mil and thicker membranes, are TPO T-Joint Covers present at field splice intersections?
- On mechanically fastened systems, are HPVX Plates fastened minimum 12" OC within the field splice?

TPC-5.1 Curb Flashing Thermoplastic

- Is 1½" hot air weld past plates and fasteners present?
- Is membrane terminated properly at the top of the curb?
 - Is counter-flashing used? If so, was it fastened with neoprene washers?
 - Are fasteners present underneath metal counter-flashing?
 - Is Water Cut-Off Mastic present?
- Membrane securement at inside angle changes?
- Are outside corners complete?
- On 60-mil and thicker membranes, have factory-fabricated T-Joint Covers been installed?
- If Termination Bar is used, follow TPC-9 Details.

TPC-6.1 Drain Details

- Are all drain bolts or clamps are in place to provide constant compression?
- Hole in membrane must be larger than drain hole itself, minimum ½" from inside the drain ring.
- Is Water Cut-Off Mastic present between the cleaned drain bowl and the membrane?
- If seams are present in drain:
 - Entire splice overlap at drain base must be hot air welded.
- Drain ring must not be broken/cracked (must be replaced if found this way).



TPC-5.1 Curb Flashing

TPC-8 Pipes/Single Penetrations

Note: Temperature of pipes must not exceed 160°F. Field-fabricated Hot Stack must be installed per Detail TPC-8.6.

Pre-molded Pipe Flashing

- Is it on a flat surface (flanges cannot be overlapped)?
- Is cut in pipe boot above rib?
- Are Water Cut-Off Mastic and clamping ring present at top of boot?

Field-fabricated Pipe Flashing


- Are two wraps present?
 - Base wrap goes up pipe ½" minimum?
 - Top wrap overlaps base wrap 1" with a 1½" minimum splice on the vertical overlap?
 - Are Water Cut-Off Mastic and clamping ring present at top of field-fabrication?
 - Fully adhered systems: Securement is needed at any pipes greater than 18" in diameter. Mechanically attached systems: securement is always required.

TPC-9 Termination Bars

- If warranty duration is 15 years or longer, Termination Bar must be present.
 - For warranties longer than 20 years, counter-flashing and Termination Bar must be used.
- Is Water Cut-Off Mastic present?
- Is Universal Single-Ply Sealant/sealant by others present at top of Termination Bar?
 - If counter-flashing is used, Universal Single-Ply Sealant/sealant by others is required at top edge of metal flashing: not on top of Termination Bar.
- Termination Bar not bent?
- Fastening of bar shall never exceed 12" OC and must always be sufficiently fastened to keep constant compression on Water Cut-Off Mastic.
- Do not wrap Termination Bar around corners. Apply on hard, smooth surfaces only: not for use on exposed wood.
 - See Detail TPC-9.5 for additional requirements if Termination Bar is used at tilt-up panel joints.
 - Water Cut-Off Mastic must be installed at approximately 10' per tube.

TPC-12 Parapet/Curb Angle Change

- Is securement present? Note: TPO Primer is required to mate membrane to PS RUSS, bonding adhesive is not acceptable.
 - Appropriate fastening rate for required warranty? No more than 12" OC.
 - 6" OC for warranty wind speeds greater than 90 mph.
- Verify all flashings are properly adhered.
- When seam is present at angle change, there must be a 1½" weld.
 - If 1½" weld is not achieved, overlay using TPO Non-Reinforced Flashing with a minimum 1½" splice in all directions around the splice.
- How is membrane terminated?
 - See Detail TPC-9.0.



TPC-12.1 Parapet Flashing

TPC-13 Tie-ins to Existing Roofing System

- Is membrane securement present?
- If the deck slopes toward the new roofing system, refer to tie-in details: Concrete Deck Termination or Weep Holes Steel Deck.
- For built-up roof tie-ins:
 - Cold Tie-in – Quick-Applied Uncured Flashing used with Two-Part Pourable Sealer.
 - Hot Tie-in – multiple layers of felt and asphalt must be used. See TPC-13.1 and TPC-13.2 Details.
- Tie-ins for existing membrane/EPDM or TPO TPC-13.3, 4, and 5:
 - PS Cured Coverstrip or field membrane in conjunction with Peel & Stick Seam Tape.
- Shingle roof tie-ins: Detail TPC-13.6 (extend above anticipated slush line).
- When tying in to PVC, a complete isolation of the system must be built and separation walls must be constructed. Liquid Flashing Detail LF-13.2 is another option to achieve tie-ins to PVC membrane.


TPC-15 Inside/Outside Corner With or Without PS Russ

- Is membrane securement present at angle change?
- Are plates and fasteners 6"-9" away from Inside/Outside Corner?
- Are plates and fasteners minimum 12" OC? Note: 6" OC must be used when warranty wind speed is greater than 90 mph. See TPC-12.0 Details.
- Pig ear fold in Inside Corner:
 - Fold on vertical wall and shedding water? 1½" weld achieved?

- When flashing Inside or Outside Corners, use one of the following:
 - TPO Inside Corners, Outside Corners or Universal Corners. TPO accessory corners are not universal.
 - Or, when cutting your own 6" x 6" TPO Non-Reinforced Flashing:
 - Flashing must be formed before application of Inside or Outside Corners. See Details TPC-15.2 and 15.4.

TPC-16.1 Molded Sealant Pockets

- For use on multiple hard-to-flash penetrations. Pipe clusters must have a minimum of 1" clearance between penetrations.
- Entire area inside Molded Sealant Pocket, as well as all penetrations, must be primed using TPO Primer or Low-VOC Primer.
- One-Part Pourable Sealer must be used: filler by others is not allowed. Is Pourable Sealer at least 2" deep?
- 1½" weld present on deck flange?
- Securement is required on mechanically fastened systems: Not required on fully adhered systems.
 - In fully adhered systems, pockets larger than 18" in diameter must have plates and fasteners.



TPC-16.1 Molded Sealant Pocket

TPC-18 Metal Scupper

- Metal scupper box must have a continuous flange with rounded corners.
- Is wood nailer present underneath metal?
- Is Water Cut-Off Mastic present underneath metal and on top of membrane?
- Is Cut-Edge Sealant present?
- Sealant by others is needed on outside of scupper where the scupper meets the outside wall.

VGC-24 Sleepers/Wood Blocking

- Are slip sheets present underneath to prevent damage to new membrane?

Check usage of Walkway Rolls.

- Present at all fixed access points, HVAC units that are regularly serviced, and concentrated walk areas?

A-27 Insulation Fastening

- Is insulation fastening in accordance with current specifications and details?
- Has proper fastener penetration been achieved?
- Reduced fastening patterns are approved on 22-gauge or heavier steel, concrete, minimum 1½" wood, and ¾" plywood decks only.