

PRODUCT SUBMITTAL




Glass Block Reinforcing (Series 200-GB)

Continuous lengths of joint reinforcement that is embedded into the horizontal mortar joints of glass block wall.



Cross welded 16" O.C. First Cross Rods welded 12" in from each end to allow lap splices per code requirements.

MATERIAL CONFORMANCE	SIZES / FINISHES								
<p>ASTM A82 / A82M - (Cold drawn steel wire) Tensile Strength - 80,000 psi Yield Point - 70,000 psi</p> <p>ASTM A951 / A91M-06 - (Standard Specification for Steel Wire for Masonry Joint Reinforcement)</p> <p>ACI / ASCE 530 - (Building code requirements for masonry structures Mill Galvanized / Zinc Coating: ASTM A641 / A641M (0.10 Oz per sq ft) Hot Dip Galvanized after fabrication / Zinc Coating: ASTM A153 / A153M-B2 (1.50 oz per sq ft) Stainless Steel ASTM 580 / 580M Type 304 (Type 316 available on special orders)</p> <p>Recycled Content: Mill Galvanized & Hot Dipped, 82.8% Post-Consumer 17% Post Industrial / Pre-Consumer,</p> <p>Stainless Steel, 97% Pre-Consumer V O C Content - 0%</p> 	<p>GLASS BLOCK REINFORCING: Manufactured to the same specifications as ladder type material except distance between longitudinal wire is 1-5/8" or 2". Continuous reinforcement ensures structurally sound glass block masonry</p> <p>Diameter: (standard) 9 ga. side rods x 9 ga. cross rods</p> <table border="0"> <tr> <td>Width:</td> <td></td> <td>Length:</td> <td></td> </tr> <tr> <td>1-5/8"</td> <td>2"</td> <td>4'</td> <td>10'</td> </tr> </table> <p>FINISHES: Mill Galvanized Hot Dip Galvanized Stainless Steel</p>	Width:		Length:		1-5/8"	2"	4'	10'
Width:		Length:							
1-5/8"	2"	4'	10'						

Corporate Office: 400 Rountree Rd Charlotte, NC 28217
TEL: (800) 849-6722 FAX: (704) 525-3761
Mailing Address: P.O. Box 240988 Charlotte, NC 28224



www.wirebond.com

Memphis Plant: 2365 Harbor Ave. Memphis, TN 38113
TEL: (800) 441-8359 FAX: (901) 775-9449
Mailing Address: P.O. Box 13124 Memphis, TN 38113