



MasterFormat: 32 12 73

FEBRUARY 2025  
(Supersedes August 2024)

# 1190

## Hot-Applied, Single-Component Joint Sealant

### DESCRIPTION

1190 is a hot-applied, single-component polymeric compound. It offers excellent cohesive and adhesive qualities – the product will not lose bond in cold weather or flow in hot weather.

### USES

1190 is developed for the economical maintenance sealing of cracks and joints in Portland cement and asphalt concrete. The product is ideal for large-scale sealing projects and is equally effective for medium-to-small-scale projects.

### FEATURES/BENEFITS

- Single-component; no mixing required.
- Offers excellent cohesion and adhesion properties.
- Will not lose bond or flow due to climatic conditions.
- Cures in less than 30 minutes.
- Applied area can be opened to traffic in 30 minutes.

### PACKAGING

30 Lb. (13.6 Kg) Cartons

### COVERAGE

Joints 1/2" (12.7 mm) wide x 1/2" (12.7 mm) deep require 13 lb. (5.9 kg) per 100 linear feet (30.5 m).

### SPECIFICATIONS/STANDARDS

- ASTM D1190-97
- ASTM D5078
- ASTM D6690, Type I
- AASHTO M 173
- Federal Specification SS-S-164

### TECHNICAL DATA

TEST	TYPICAL RESULTS
Penetration, mm/10	70 max
Flow, cm	0.1 - 0.2
Bond test, 50% extension @ 0° F (-18° C), 5 cycles	Pass
Viscosity @ 370° F (188° C), CPS	5000 - 7000
Wt. per gallon, lb.	10
Wt. per liter, kg.	1.20
Recommended pouring temp.	370° F (188° C)
Recommended safe heating temp.	390° F (199° C)

### APPLICATION

**Melting** ... 1190 should be melted in an oil-jacketed melter-applicator with an agitator and separate temperature thermometers for oil bath and melting vat.

**Surface Preparation** ... The joints and cracks to be sealed must be clean and dry. Dust, dirt and laitance should be removed prior to application. Proper routing should be slightly larger than the existing crack/joint to ensure proper adhesion to sidewalls.

NOTE: Application of sealant into frozen or wet pavement will result in loss of bond and premature failure of the sealant.

**New Concrete Pavement Sealing** ... Typical joint configuration should be 1/2" (12.7 mm) wide with a 1/2" (12.7 mm) depth for an approximate 1:1 width to depth ratio. Designated joint width and depth is determined by the appropriate highway or pavement authority. CERA-ROD™ heat-resistant backer rod from W. R. MEADOWS may be installed in the joint opening to control depth and sealant usage.

CONTINUED ON REVERSE SIDE ...

## Asphalt Pavement and Maintenance

**Sealing** ... For ideal sealing with maximum effectiveness, it is suggested that cracks or joints be routed out to provide a sealant reservoir 1/2" (12.7 mm) wide with a minimum depth of 1/2" (12.7 mm). This provides for a 1:1 width-to-depth ratio. For joints 1" (25.4 mm) wide, the suggested depth is 1/2" (12.7 mm) minimum. To control and maintain the suggested joint depth and sealant usage, CERA-ROD heat-resistant backer rod may be installed in the joint opening.

### Application Method

Sealing may be done at air temperatures of 40° F (4° C) and higher. The sealant should be applied into the crack/joint, slightly overfilling. Once applied, a follow-up should be done with a soft rubber, U-shaped squeegee to form a wipe zone of approximately 3 - 4" (76.2 - 101.6 mm) wide along the crack/joint and flush with the highway or pavement surface.

### PRECAUTIONS

Application life may be extended by adding fresh material as sealant is applied and the quantity in the kettle decreases. 1190 hot-pour joint sealant can be reheated once within the prescribed safe heating temperature limits. Repeated reheating may result in material degradation or gelling in the melter. When the application life has been exceeded, 1190 will thicken, become stringy, and may gel. If this occurs, remove the sealant immediately from the kettle and discard.

Read and follow application information and use in accordance with the health and safety information shown on the label. Refer to Safety Data Sheet for complete health and safety information.



W. R. MEADOWS®

**Prevent.  
Protect.  
Preserve.**



#### LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

#### Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.