



MasterFormat: 03 39 23

JANUARY 2019
 (Supersedes August 2016)

CS-309™-OTC

Acrylic, Non-Yellowing Curing and Sealing Compound

DESCRIPTION

CS-309-OTC acrylic concrete curing and sealing compound is an acrylic polymer solution. In addition to regular concrete, the product can also be used for decorative concrete needs. CS-309-OTC provides a tough, clear film that will not after-yellow. It also provides improved weather and stain resistance, combined with a dustproof sealer.

USES

CS-309-OTC is used on driveways, patios, loading docks, swimming pool areas, and exposed aggregate, as well as any exterior decorative surface where enhanced appearance, protection, and sealing of concrete is desired (dries to a low-medium sheen). (Higher gloss films can be achieved with additional applications.) CS-309-OTC offers improved resistance to rain, sun, freezing temperatures, stains, oil, grease, de-icing salts, cleaning agents (except aromatic solvents), and caustics, as well as airborne soot, dust, and other pollutants.

FEATURES/BENEFITS

- Specifically formulated to enhance the appearance of colored and architectural concrete.
- Permeable film allows moisture in cured concrete to evaporate.
- Provides a clear, tough, easy-to-clean film which improves abrasion and stain resistance.
- Ultraviolet stable; non-yellowing under extreme exposure.
- Offers improved resistance to rain, sun, freezing temperatures, oil, grease, de-icing salts, cleaning agents (except aromatic solvents), caustics, airborne soot, dust, and other pollutants.
- Offers excellent foot or vehicular traffic wearing qualities.
- Recoat after thorough surface cleaning to restore the original beauty.
- Applies easily ... dries quickly for less down time.
- Concrete sealed with CS-309-OTC can later be painted (consult reputable paint manufacturer for compatibility) or covered with resilient flooring or carpeting, if desired.
- Dried film is USDA accepted.
- VOC compliant.

PACKAGING

1 Gallon (3.78 L) Cans
 5 Gallon (18.9 L) Pails
 55 Gallon (208.2 L) Drums

SPECIFICATIONS

- AASHTO M 148, Type 1, Classes A & B
- ASTM C309, Type 1, Classes A & B
- Complies with National AIM, LADCO, and Phase I OTC states VOC regulations.

COVERAGE

300 - 600 ft.²/gal. depending on surface finish. Coverage is approximate and may vary depending on surface finish/texture, concrete condition, climatic conditions, etc. Always apply to a test area first to determine actual coverage rate before full-scale application.

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 40° - 90° F (4° - 32° C), optimum performance and best use is obtained within two years of date of manufacture.

TECHNICAL DATA

VOC Content: 346 g/L

APPLICATION : Surface Preparation

Fresh (New) Concrete ... Apply as soon as all surface water has disappeared and the concrete surface will not be marred by walking workers.

Existing (Old) Concrete ... Concrete surface must be clean and dry with all stains, oil, grease, dust, dirt, and curing compounds removed prior to application.

Application Method ... Use a sprayer or short-nap roller to apply a uniform film. Avoid puddling in low areas. If puddles occur, brush or roll them out. A standard industrial-grade sprayer, such as a Chapin 19069,

CONTINUED ON THE REVERSE SIDE...

W. R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338
 Phone: 847/214-2100 • Fax: 847/683-4544
 1-800-342-5976
 www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
 FORT WORTH, TX / BENICIA, CA / POMONA, CA
 GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

equipped with Viton fittings and a spray nozzle that produces a flow of 0.5 GPM (1.9 LPM) under 40 psi (0.276 MPa) of pressure, is recommended. Apply over the entire surface; avoid puddling in low areas.

For ultimate protection on new concrete, use the W. R. MEADOWS complete curing-and-sealing system. First, apply a uniform film of CS-309-OTC as soon as possible after the surface water has disappeared and the concrete surface will not be marred by walking workers. After this first application has thoroughly dried, then apply TIAH® OTC from W. R. MEADOWS using a sprayer or short-nap roller. This combination will create a superior, durable, long-lasting surface. If future reapplication of a sealer is required, use TIAH OTC.

For full application guidelines, please visit <https://www.wrmeadows.com/training-videos/otc-product-application-guidelines/>.

Mixing ... For optimum performance, gentle mixing or agitation is recommended. CAUTION: TO AVOID FOAMING, DO NOT MIX EXCESSIVELY.

Drying Time ... Product dries quickly. Drying times will vary depending on application rate, temperature, humidity, and project conditions. Restrict foot traffic for at least four hours. Twelve hours is preferable.

Cleanup ... Clean tools after use with a solvent such as xylene, toluene, or SEALTIGHT CLEANER from W. R. MEADOWS.

PRECAUTIONS

FOR OUTSIDE/EXTERIOR APPLICATION ONLY. CS-309-OTC IS FLAMMABLE. KEEP AWAY FROM ALL OPEN FLAMES, SPARKS, IGNITION SOURCES, etc. Use with adequate ventilation and block all HVAC ventilation ducts which may spread product vapors - vapors are flammable and heavier than air. If product odors are objectionable, W. R. MEADOWS recommends using a water-based product, such as DECRA-SEAL™ W/B or any of the VOCOMP® series products. CS-309-OTC must be applied without diluting or thinning. Surfaces treated with CS-309-OTC may become slippery under certain conditions.

To increase slip resistance, addition of SURE-STEP™ from W. R. MEADOWS is recommended. CS-309-OTC should not be applied in direct sunlight, or in high temperature conditions. These conditions cause rapid evaporation, preventing proper film formation, which may cause the dried film to peel, bubble, become hazy, and/or turn white (blush). Surface temperature of the concrete must be between 40° - 90° F (4° - 32° C) at time of application to allow for proper film formation.

CS-309-OTC should not be applied to concrete exposed to excessive moisture. Entrapped moisture in a solvent-based sealer may cause the film to peel and/or turn white (blush). Improper or over-application may cause the dried CS-309-OTC film to appear hazy and/or white.

Product may be used on colored concrete, but mottling may occur. Do not use on dense or non-porous surfaces, i.e. brick, stone, etc. Concrete containing calcium chloride will remain dark longer when treated with this product. Concrete floors properly sealed with CS-309-OTC meet the requirements of ASTM C1315, Section 8.8 - Adhesion, for ceramic tile adhesives per ANSI A 136.1-1992 requirements. For any other specifications, applications, installations, etc., please obtain approval for use from the manufacturer of the subsequent product/treatment being applied. These products may include, but are not limited to adhesives, mortars, tile cements, paints, coatings, penetrating treatments, etc. The specifier and user shall determine the suitability of product for specific applications and assume all responsibility in connection therewith.

LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management

For most recent data sheet, further LEED information, and safety data sheet, visit www.wrmeadows.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control

over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.