



MasterFormat: 07 14 13

APRIL 2025
(Supersedes August 2024)

HRM 714

Hot-Applied Rubberized Waterproofing Membrane

DESCRIPTION

HRM 714 hot-applied rubberized asphalt waterproofing membrane is a 100% solids blend of asphalts, synthetic rubber polymers, and fillers formulated to provide toughness with flexibility and low moisture vapor permeance.

USES

HRM 714 is hot-applied to form a continuous elastomeric membrane. It is ideal for use on plaza and outdoor amenity spaces, protected membrane roofing assemblies (PMRA), split-slab and parking decks, tunnels and bridge decks, and similar types of construction where a monolithic waterproofing membrane is desirable.

FEATURES/BENEFITS

- Excellent combination of toughness and low temperature flexibility.
- Very low water absorption and vapor permeance.
- 0 g/L VOC
- Resistant to chemicals, acid, fertilizer, and salt water.

PACKAGING

30 Lb. (13.6 Kg) Cartons

COVERAGE

Thickness (Mils)	Application Rate	Coverage
1 st Layer 90	0.51 lb./ft. ² (2.52 kg/m ²)	57.2 ft. ² (5.19 m ²)
2 nd Layer 125	0.72 lb./ft. ² (3.5 kg/m ²)	41.6 ft. ² (3.86 m ²)
Total Installed 215	1.23 lb./ft. ² (6 kg/m ²)	24.4 ft. ² (2.26 m ²)

Coverage is expressed as an average and is dependent upon surface conditions.

SHELF LIFE

Five years in unopened container.

SPECIFICATIONS/STANDARDS

- LA Research Report RR 26213
- UL790 Class A Certification – File No. R41353

TECHNICAL DATA

PROPERTY	TYPICAL TEST RESULT	TEST METHOD
Solids Content	100%	ASTM D1353
Typical Application Thickness	Fabric Reinforced Assembly: 215 mils total (90 mils/125 mils)	
Water Resistance	No delamination, blistering, emulsification, or deterioration	CGSB-37.50-M89
Low Temperature Crack Bridging Capability	Pass at >0° F (-17.8° C)	CGSB-37.50-M89
Heat Stability	Pass	CGSB-37.50-M89
Pull off Strength, lbf	108	ASTM D4541
Flow	0.2 cm	ASTM D1191, CGSB-37.50-M89
Penetration @ 32° F (0° C) @ 77° F (25° C) @ 122° F (50° C)	25 mm 55 mm 160 mm	ASTM D1191 CGSB-37.50-M89
VOC Content	0	ASTM D2369
Water Absorption	0.20 g weight gain	CGSB-37.50-M89
Viscosity	5.0 to 7.0 seconds	CGSB-37.50-M89
Adhesion to Concrete	Pass	ASTM D3408, CGSB-37.50-M89
Softening Point	200° F (93° C)	ASTM D36
Elongation	1,500%	ASTM D1191
Water Vapor Permeance	0.019 Perms	ASTM E96, Method B
Tensile Strength, psi (MPa)	26 (0.17)	ASTM D412
Acid Resistance	50% Sulfuric Acid w/o blistering, deterioration, delamination or re-emulsification	ASTM D896 Procedure 7.1 (N-8)
Salt Water Resistance (20% sodium carbonate and calcium chloride)	Passed 20% Sodium Chloride w/o blistering, deterioration, delamination or re-emulsification	ASTM D896 similar
Fertilizer Resistance (undiluted 15/5/5 nitrogen /phosphorus/potash)	Passed 30/10/10 Fertilizer w/o blistering, deterioration, delamination or re-emulsification	ASTM D896 similar
Animal Waste Resistance, 3-year exposure	No deterioration	

CONTINUED ON REVERSE SIDE ...

W. R. MEADOWS, INC.

P.O. Box 338 • Hampshire, IL 60140-0338
Phone: 847/214-2100 • Fax: 847/683-4544
1-800-342-5976
www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
FORT WORTH, TX / BENICIA, CA / POMONA, CA
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

TECHNICAL DATA (continued)

PROPERTY	TYPICAL TEST RESULT	TEST METHOD
Bond to Concrete @ 0° F, (18° C)	Pass	ASTM D3408
Water Vapor Transmission	1.7 ng/Pa*s*m ² maximum	ASTM E96 Procedure E
Asphalt Compatibility	Pass	ASTM D5329

APPLICATION

Surface Preparation ... Prior to commencement of the waterproofing application, the following preparation may be necessary:

Chip or grind off concrete spills from subsequent pours to create a flat, uniformly smooth surface. Fill depressions in the concrete left by form boards, footprints, screed rail chairs, etc. with MEADOW-PATCH® 5 from W. R. MEADOWS. Remove areas of heavy laitance with a grinder, brush hammer, scabbler, or similar device.

Grind off sharp projections, fishtails, and sharp corners. Patch honeycombed or bug-hole areas with MEADOW-PATCH 5.

On existing structures, remove old waterproofing. Remove lightly scaled concrete down to sound concrete and restore to proper cross section and grade with a Portland cement mixture. Where scaled and spalled concrete exposes reinforcing steel, remove concrete to below exposed steel and replace with MEADOW-CRETE® GPS from W. R. MEADOWS.

Do not use hot-mix patching to level up a deck prior to waterproofing.

Concrete surface suitable for membrane application should be wood-float finish or broom finish and be clean and free of oil, grease, curing compounds, dampness, frost, dust, or loose particles that can impair bond of the HRM 714 system to substrates. Sand-blasting and vacuuming are recommended after which no traffic should be permitted in the area.

For proper surface conditioning application and techniques, contact W. R. MEADOWS technical services.

Cracks, Joints, Other Discontinuities ... Cracks and construction joints that are 1/16" (1.6 mm) and 1/8" (3.2 mm) shall be coated with a 125-mil application of HRM 714. Immediately embed a 6" (150 mm) wide strip of REINFORCING FABRIC HCR into membrane while hot. Brush to ensure full contact of fabric with membrane including all side and end laps and eliminate any wrinkles. Lap all ends of fabric a minimum of 2" (50.8 mm) with hot-applied membrane. 1/8" (3.2 mm) to 1/2" (12.7 mm) cracks and construction joints shall be coated with 125-mil application of HRM 714. Immediately embed a 6" (150 mm) wide strip of NEOPRENE FLASHING MEMBRANE from W. R. MEADOWS or acceptable sand/sand modified asphalt flashing. Ensure full contact of flashing while membrane is still warm and tacky. Lap all ends of neoprene or modified flashings a minimum of 6" (150 mm) with hot-applied membrane. Cracks and joints less than 1/16" (1.6 mm) do not require reinforcement. Reinforce static inside and outside corners with a 125-mil coating HRM 714 and immediately embed a 6" (150 mm) strip of REINFORCING FABRIC HCR centered on the apex of the corner. Brush to ensure full contact of fabric with membrane including all side and end laps and eliminating any wrinkles.

Expansion Joints ... For expansion joints 1/2" - 2" (12.7 - 50.8 mm), apply a 125-mil (3 mm) thick coating of HRM 714 8" (203.2 mm) wide to both sides of joint. Immediately embed 6" (152.4 mm) of NEOPRENE FLASHING MEMBRANE onto each side of joint into hot membrane. Drape flashing into joint to a depth of 1.5" (38.1 mm) or enough to accommodate movement.

Surface Conditioning ... Apply either ASPHALT PRIMER/CONDITIONER (solvent-based) or SURFACE PRIMER/CONDITIONER (water-based) from W. R. MEADOWS to all surfaces to receive HRM 714 hot-applied waterproofing at a coverage rate of 250 - 300 ft.²/gal (6.14 - 7.37 m²/L). Ensure adhesive is tack-free before application of HRM 714.

Flashing ... Clean all metal surfaces free from rust and debris to receive hot-applied membrane, including flashings, vents, drains, etc., with solvent, dry with clean cloths, and condition with ASPHALT PRIMER/CONDITIONER solvent-based adhesive. Allow the solvent-based adhesive to dry before applying HRM 714 membrane.

NEOPRENE FLASHING MEMBRANE is used for flashing of drains, curbs, cold joints, transitions and penetrations. NEOPRENE FLASHING MEMBRANE is also used for expansion joints from 1/2" (12.7 mm) to a maximum of 2" (50.8 mm).

Expansion joints greater than 2" (50.8 mm) require a 3rd-party joint system that designed to be incorporated with hot fluid-applied rubberized asphalt waterproofing.

Vertical Surfaces ... Apply a uniform 90-mil (3 mm) base coating a minimum of 8" (200 mm) vertically as required by Code and 3" (75 mm) horizontally onto the structural deck. Immediately embed REINFORCING FABRIC HCR into membrane while still hot, ensuring the correct 2" (50.8 mm) minimum overlaps. Brush fabric reinforcement to eliminate wrinkles. Apply the second 125-mil (2.3 mm) application of HRM 714 uniformly onto reinforcement fabric. Immediately apply the 94-mil PC2R PROTECTION COURSE from W. R. MEADOWS into membrane while the second layer of HRM 714 is still hot. Ensure 2" (50.8 mm) side laps and 6" (152.4 mm) laps at end laps. Terminate the completed hot fluid-applied waterproofing system on vertical surfaces with TERMINATION BAR by W. R. MEADOWS or into a 1/2" x 1/2" (12.7 mm x 12.7 mm) reglet.

Drains ... Apply 125 mils (3 mm) of HRM 714 onto the drain receiver cast into the deck and extend a minimum of 6" (152.4 mm) past the edge of drain receiver onto concrete deck. Immediately embed NEOPRENE FLASHING MEMBRANE into hot membrane up to the throat of drain opening.

Panelized Deck Application ... Cover all static joints between ends and edges of gypsum roof cover boards or plywood sheets with a minimum 6" (150 mm) wide, 125-mil (3 mm) coating of HRM 714. Immediately embed a 6" (150 mm) strip of REINFORCING FABRIC HCR centered over joints into hot membrane. Embed with a brush to eliminate wrinkles. Upon completion of joint and detail flashing work, apply a uniform 90 mil base layer (2.3 mm) of HRM 714 evenly, covering all previously installed flashings and reinforced areas. Immediately embed REINFORCING FABRIC HCR into membrane while still hot, ensuring a minimum 2" (50 mm) overlap at all side and end laps and full membrane engagement at all end and side laps. Brush reinforcing fabric into membrane to ensure full embedment and eliminate wrinkles. Apply the second layer of hot-applied membrane at a uniform thickness of 125 mils (3 mm) to achieve a total system thickness of 215 mils (5.5 mm).

Upon application of the second and final ply of hot-applied membrane, install the rolled PC2R PROTECTION COURSE into the membrane while it is still hot. For areas requiring high compressive strength or vehicular traffic over concrete topping slabs, the mineral-fortified PC-2 or PC-3 PROTECTION COURSE from W. R. MEADOWS should be considered.

Where asphaltic concrete road paving asphalt is specified immediately on top of installed HRM 714, 1/4" (6.4 mm) PROTECTION COURSE shall be used as the protection layer. Immediately set PC-2 PROTECTION COURSE onto the second layer of HRM 714 while it is still hot. Butt all side and ends of PC-2 tightly together leaving. Joints may also be reinforced with cut 4" (102 mm) wide strips of the 65-mil self-adhering membrane MEL-DEK™ from W. R. MEADOWS.

Protection ... Upon completion of the waterproofing system application, immediately install the overburden as specified. Where extended delays installing the overburden occur, protection of the completed waterproofing system is advised. Use of 3/4" (19 mm) plywood is recommended where heavy wheeled equipment and prolonged trade work foot traffic is anticipated on top of the completed waterproofing system.

PRECAUTIONS

Do not heat HRM 714 membrane greater than 410° F (210° C). HRM 714 is not compatible with coal tar pitch, nor is it recommended over lightweight, non-structural concrete.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.