



MasterFormat: 07 13 26

NOVEMBER 2022  
(Supersedes April 2020)

## MEL-ROL® LIQUID MEMBRANE

### Two-Component Detailing Membrane

#### DESCRIPTION

MEL-ROL LIQUID MEMBRANE is a two-component, 100% solids, cold-applied, non-slump detailing material that can be used for a variety of applications in the MEL-ROL waterproofing system. MEL-ROL LIQUID MEMBRANE cures to form a tough, flexible membrane.

#### USES

MEL-ROL LIQUID MEMBRANE can be used in the forming of fillets and reinforcement at corners and as a flashing material.

#### FEATURES/BENEFITS

- 100% solids.
- Suitable for use underneath MEL-ROL membrane.
- Cures to a tough, flexible membrane.

#### PACKAGING

1 Gal. (3.78 L) Units

#### COVERAGE

20 - 25 ft.<sup>2</sup>/gal. (0.49 – 0.61 m<sup>2</sup>/L) @ 60 mils.

As a corner reinforcement and fillet, approximately 14 lineal ft./gal. (1.1 m/L). For a 3" (76.2 mm) flashing, approximately 17 lineal ft./gal. (1.4 m/L). As a fillet, approximately 135 lineal ft./gal. (10.9 m/L).

Coverage dependent on substrate type, weather, and application conditions.

#### SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 40° - 90° F (4° - 32° C), optimum performance and best use is obtained within two years of date of manufacture.

#### TECHNICAL DATA

VOC Content: 0 g/L

#### SPECIFICATIONS/STANDARDS

- Complies with all current federal, state, and local maximum allowable VOC requirements, including National EPA VOC Emission Standard for Architectural Coatings, CARB, Colorado AIM, LADCO, Maricopa County, OTC Phase I and II, SCAQMD, and Utah Department of Air Quality.

#### APPLICATION

**Surface Preparation** ... All surfaces to be covered with MEL-ROL LIQUID MEMBRANE should be clean, free of all contaminants, dry, and frost-free.

**Mixing** ... The entire amount of pre-measured activator should be poured into the base material and blended together. Mix with a slow speed, heavy-duty drill equipped with a flat mixing paddle. Start slowly to avoid splashing and mix for a minimum of five minutes. Be sure to scrape the sides and bottom periodically to assure complete blending.

**Application Method** ... Trowel on MEL-ROL LIQUID MEMBRANE to a minimum thickness of 60 mils. MEL-ROL LIQUID MEMBRANE may be applied to both primed and unprimed concrete surfaces. Apply in 3" (76.2 mm) or 4" (101.6 mm) wide strips of material over terminations. When used as a corner reinforcement, apply a minimum of 6" (152.4 mm) wide in each direction. When used as a fillet, the face should be a minimum of ¾" (19.1 mm). At drains and protrusions, MEL-ROL LIQUID MEMBRANE should overlap the MEL-ROL at a minimum of 2" (50.8 mm) and should extend 6" (152.4 mm) above the surface or to the top of the wearing course. If applying fresh material over the cured membrane, the cured membrane should be lightly washed and wiped with an aromatic solvent. Allow for a few minutes to dry and trowel on the fresh material. If applying fresh material over the cured membrane, the cured membrane should be lightly washed and wiped with an aromatic solvent. Allow for a few minutes to dry and trowel on the fresh material.

CONTINUED ON REVERSE SIDE ...

#### W. R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338  
Phone: 847/214-2100 • Fax: 847/683-4544  
1-800-342-5976  
www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA  
FORT WORTH, TX / BENICIA, CA / POMONA, CA  
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

**Curing Time** ... Mixed material must be applied in 1 ½ hours. (Application time will be shorter at elevated temperatures.) Discard material that begins to thicken and becomes difficult to apply. MEL-ROL LIQUID MEMBRANE will cure overnight to form a tough, flexible membrane.

**Cleanup** ... Tools can be cleaned with an aromatic solvent. Follow manufacturer's precautions when using a solvent for cleanup.

## PRECAUTIONS

Do not mix partial units. Allow membrane to cure for 24 hours before flood testing. For easier mixing and application, store at temperatures of 60° F (15.6° C) or higher. Refer to Safety Data Sheet for complete health and safety information.



### LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

### Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.