



MasterFormat:

03 01 00

03 64 23

AUGUST 2022

(Supersedes September 2013)

REZI-WELD™ LV STATE

Ultra-Low Viscosity Injection Epoxy

DESCRIPTION

REZI-WELD LV STATE is an ultra-low viscosity, two-component, 100% solids, rapid setting, epoxy-based, structural injection resin. It is a solvent-free, low odor, high strength, high modulus, moisture-insensitive, ultra-low viscosity epoxy resin system. REZI-WELD LV STATE resists most chemicals and forms a structural, monolithic bond with typical concrete.

Its low surface tension facilitates deep penetration into hairline to medium-sized cracks. The 100% solids formulation is volumetrically stable, ensuring a solid bond to both sides of the crack.

USES

REZI-WELD LV STATE is designed for gravity feeding or pressure injecting. It is available in two cartridge sizes for ease of use. It is also available in bulk units and may be injected using two-component metering pumps. It is suitable for injecting fine, non-moving structural cracks in concrete and wood for long-term repairs. REZI-WELD LV STATE makes an economical, easy-to-use epoxy mortar for patching or repairing defects in concrete substrates.

FEATURES/BENEFITS

- Ultra-low viscosity is ideal for pressure injection and gravity feeding.
- Advantageous as a low viscosity, epoxy adhesive binder.
- Bonds cured concrete to wood, steel, or freshly placed concrete.
- Combines with aggregate to form an interior, non-skid topping.
- Resists industrial chemicals, as well as impact and attack from moisture.
- Features low-viscosity, high-modulus, high-strength, self-leveling characteristics.
- Furnished in two convenient cartridge sizes.

PACKAGING

- 6.1 Oz. (180 mL) Cartridge
- 16 Oz. (475 mL) Cartridge
- 3 Gallon (11.4 L) Unit
- 15 Gallon (57 L) Unit

COVERAGE

One gallon (3.8 L) neat covers approximately 85 -100 ft.²/gal. (2.1 - 2.7 m²/L), depending on surface porosity and end use application. One gallon (3.8 L) mixed 1:1 with dry aggregate yields approx. 350 in.³ (5735 cm³) of grout.

SHELF LIFE

Two years in unopened containers and cartridges when stored between 50° - 95° F (10° - 35° C).

SPECIFICATIONS/STANDARDS

- ASTM C 881-99 Type I, II, IV and V, Grade 1, Classes B & C
- AASHTO M 235 Type I, II, IV and V, Grade 1, Classes B & C
- Various departments of transportation approvals

CONTINUED ON REVERSE SIDE ...

W. R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338
Phone: 847/214-2100 • Fax: 847/683-4544
1-800-342-5976

www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
FORT WORTH, TX / BENICIA, CA / POMONA, CA
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

TECHNICAL DATA

All technical data is typical information, but may vary due to testing methods, conditions, and operators.

Property	Typical Data	Test Method
7 Day Cure @ 77° F (25° C) Viscosity, cps	450 - 550	ASTM C881
Tensile Strength, psi	7,200 (49.6 MPa)	ASTM D638
Elongation, %	8.8	ASTM D638
Hardness, Shore D	85	ASTM D2240
Flexural Strength, psi	8500 (55.2 MPa)	ASTM D790
Compressive Yield Strength, psi	12,000 (82.7 MPa)	ASTM D695
Compressive Modulus, psi	260,000 (1,800 MPa)	ASTM D695
Bond Strength, psi (2 days)	2,100 (14.4 MPa)	ASTM C882
Bond Strength, psi (14 days)	3,000 (20.6 MPa)	ASTM C882
Heat Deflection Temperature	120° F (48° C)	ASTM D648
Absorption, % (24 hours)	0.23%	ASTM D570
Linear Coefficient of Shrinkage	0.004	ASTM D2566
Component Properties	Resin	Hardener
Mix Ratio (PBV = Parts by Volume)	2 PBV	1 PBV
Appearance	Clear	Amber
Pot Life (1000 gms) @ 75° F (21.5° C)	20 - 30 Min.	ASTM C881
Tack-Free Time @ 30 mils @ 700 F (21.1° C)	4 - 5 Hrs.	ASTM C879
VOC Content	5 g/L	

APPLICATION

Surface Preparation ... All surfaces to be bonded must be free of standing water and completely clean of dirt, rust, curing compounds, grease, oil, paint, waxes, and other materials which would prevent an optimal bond. Concrete should be prepared by mechanical abrading or high-pressure water jetting to a sound surface. Vacuum or blow dust away with oil-free, compressed air. Mechanically abrade metal base plates to a bright metal finish. Exposed steel surfaces should be sandblasted and vacuumed clean; if not possible, degrease the surface and use sandpaper or a wire brush to reveal continuous, bright metal.

Mixing ... The resin and hardener (contained in the cartridge) must be conditioned between 65° - 85° F (18° - 29° C) at the time of application. Use the double-boiler method or store material in a warm room prior to application. Shake the cartridge vigorously for 60 seconds then stand the cartridge upright for 60 seconds, allowing the bubbles to rise to the top.

APPLICATION METHOD

1. Substrate temperature must be 40° F (4° C) and rising at the time of application.
2. Ensure static mixer nozzle is free of obstructions.
3. Remove nose cap.
4. Remove nose plug.
5. Insert static mixer onto cartridge nose. Slide retaining nut (located in sealed bag) down static mixer shaft.
6. Tighten retaining nut onto cartridge nose.
7. Load into standard dual cartridge dispenser tool.
8. Dispense and discard approximately a 3" (73.2 mm) bead of material until a uniform amber color is achieved.
9. Re-insert nose plug and seal with nose cap to seal a partially used cartridge.
10. Follow all instructions prior to application of partially used cartridge.

Crack Injecting ... Epoxy can be pressure injected into fine cracks that are small (1/8" [3.2 mm] maximum width). Surface seal the crack and set the REZI-WELD injection ports using REZI-WELD GEL PASTE STATE or POLY-GRIP™ from W. R. MEADOWS. Allow sufficient time for the surface seal to harden prior to injecting. If using one of the two cartridges, always use a high ratio application gun having a 35:1 ratio mechanical advantage.

Gravity Feed ... Seal underside of elevated slab prior to filling if cracks reflect full depth. Pour neat, properly mixed and conditioned REZI-WELD LV STATE into v-notched crack. Continue placement until completely filled.

Interior, Non-Skid Topping ... Apply at a rate not to exceed 100 ft.²/gal. (2.7 m²/L). Then apply layer of sand or grit over epoxy and allow epoxy to cure. Blow or vacuum excess sand away. NOTE: REZI-WELD LV STATE IS NOT TO BE USED AS A FINISHED FLOOR COVERING OR PROTECTIVE TREATMENT.

Aggregates for Epoxy-Resin Mortars ... Combine clean, dry aggregates with freshly mixed epoxy in a ratio of one part epoxy to 4 - 5 parts, by volume, of graded aggregates (not to exceed six parts sand). Patch thickness should not exceed 1.5" (50.5 mm) per lift.

Cleanup ... Clean tools and equipment immediately with toluene or xylene. Clean equipment away from all ignition sources and avoid breathing vapors or allowing epoxy-containing solvent to contact skin. Should this material come in contact with skin, wash thoroughly with soap and water, not solvent.

PRECAUTIONS

DO NOT DILUTE. Mix complete units only. Not recommended for use when the concrete temperature has been below 40° F (4° C) for the past 24 hours. Do not use to seal cracks under hydrostatic pressure. Do not warm epoxy over direct heat. REZI-WELD LV STATE is not to be used as an exterior coating, as it is not resistant to ultraviolet rays. Do not use when substrate temperature at time of application is above 110° F (43° C).

HEALTH AND SAFETY

This epoxy is corrosive. Personal protective equipment is necessary. Unused epoxy will generate excessive heat, especially in large quantities. Unused epoxy should be mixed with dry sand in the container to help lower heat. Refer to Safety Data Sheet for complete health and safety information.

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.